

# 5440 PU66 8H PU Topcoat Gloss

## TECHNICAL DATA SHEET

### Product Description

5440 is a two component polyurethane topcoat of the PU66 range, designed for the internal / external protection and decoration of aircraft structures.

- Conventional solids
- Excellent fluid resistance including Skydrol, hydraulic fluids
- Outstanding UV and long term durability

### Components

#### Mix Ratio (by volume)

Component Ref.	Spray Application	Brush Application
5440/.... (Base)	1	5
07309000 (Activator)	1	NOT APPLICABLE
07079000 (Activator)	NOT APPLICABLE	2
04919000 (Thinner)	TO VISCOSITY	NOT APPLICABLE

### Specifications



5440 is qualified to:

- AIMS 04-04-003
- AIMS 04-04-012
- ASNA 3626
- ASNA 4247
- BLGG 140301
- HMDC0055
- HMRC0060
- MDL 5041

5440 meets the performance requirements of:

- Mil-PRF-85285

#### Product Compatibility

5440 is compatible with the following primer specifications :

- AIMS 04-04-002
- AIMS 04-04-003
- AIMS 04-04-011
- ASNA 4251
- BLGG 0900101
- AIMS 04-04-012

# 5440 PU66 8H PU Topcoat Gloss

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

## Surface Preparation and Pretreatment



Ensure surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Observe recommended over coating windows for primers. For further information refer to the technical data sheet for the relevant primers.

## Instructions for Use



Base component may require mechanical agitation. Ensure all components are adequately dispersed. Before adding the activator to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Slowly add activator to base while stirring, then add required thinner (spray application only) while stirring.

*Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**


Not required



### **Viscosity:** (21 - 25°C / 70 - 77°F)

• AFNOR 2.5	45 - 55 seconds
• AFNOR4	14 - 16 seconds
• BSB3	23 - 30 seconds
• BSB4	18 - 20 seconds
• FORD4	13 - 15 seconds
• ISO3	30 - 50 seconds
• ISO4	17 - 22 seconds
• ZAHN2	15 - 20 seconds

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

8 hours @ 21 - 25°C (70 - 77°F)

# 5440 PU66 8H PU Topcoat Gloss

## Application Guidelines

### Recommended Application Conditions:

Temperature 15 - 35°C (59 - 95°F)  
Relative Humidity 30 - 85%

### Application:

Apply 2 cross coats to achieve the recommended dry film thickness.




### Theoretical Coverage: (unthinned)

6 - 8 m<sup>2</sup>/Lt @ 40 µm dry film thickness  
240 - 320 ft<sup>2</sup>/US gal @ 1.6 mil dry film thickness

### Recommended Dry Film Thickness:

30 - 50 µm  
1.2 - 2 mil



### Dry Film Density:

1.2 - 1.6 g/cm<sup>3</sup> (depending on colour)  
10.2 - 13.3 lbs/US gal

### Dry Film Weight:

47 - 64 g/m<sup>2</sup> @ 40 µm dry film thickness  
0.009 - 0.013 lbs/ft<sup>2</sup> @ 1.6 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

### Equipment:



Equipment Type	Tip Size (mm)	Pressure
HVLP Air Spray	1.2	22 to 29 psi (1.5 to 2 bar)
Pressure Pot	1.5	43 to 72 psi (3 to 5 bar)



5440 can also be applied by brush (refer mix ration table).



### Equipment Cleaning:

Clean application equipment before use and as soon as possible after use. DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended.

# 5440 PU66 8H PU Topcoat Gloss

## Physical Properties



**Colour:**

This product is available in a wide range of colours. Please contact PPG Aerospace to discuss specific requirements.




**Gloss:**

>90 units with a 60° gloss meter



DRYING TIMES @ 50 % R.H	23°C (73°F)	60°C (140°F)
Dust Free	2 hours	
Dry to Handle	5 hours	
Dry to Tape	8 hours	30 minutes
Dry to Overcoat	1 hour (min.) 72 hours (max.)	15 minutes
Full Cure	7 to 9 days	

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



**Flash Off Time:**

15 - 30 minutes prior to force dry.



**VOC: (ASTM)**

Mixed ready for use (unthinned)	<600 g/Lt
5440 Base Component	<500 g/Lt
0730/9000 Activator	705 g/Lt
0707/9000 Brush Activator	460 g/Lt
0491/9000 Thinner	840 g/Lt



**Flash Point:**

5440 Base Component	26°C (79°F)
0730/9000 Activator	13°C (55°F)
0707/9000 Brush Activator	50°C (122°F)
0491/9000 Thinner	-2°C (28°F)

## 5440 PU66 8H PU Topcoat Gloss

### Shelf Life:

5440 Base Component	24 months in original unopened container
0730/9000 Activator	24 months in original unopened container
0707/9000 Brush Activator	24 months in original unopened container
0491/9000 Thinner	10 years in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

### Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions*



# 5440 PU66 8H PU Topcoat Gloss

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

**Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 06/18  
Lit: 4209