

0986/2620 Anti-Static Type II Kit

TECHNICAL DATA SHEET


Product Description

0986/2620 is the kit reference for 5420/2620 anti-static polyurethane primer base & activator. This product is designed to conduct the electrostatic charges from composite parts to the metallic structure of aircraft.

- Type II Low conductivity for use on radomes & antenna fairings
- Compatible with most types of composite materials
- Sandable
- Good flexibility
- Water resistant
- Electrical Resistivity 5-100 MΩ per square

Components

Kit 0986/2620 (3 Ltr 5420/2620 + 1 Ltr 0709/9000)



Mix Ratio (by volume)

- | | |
|-------------------------|---------|
| • 5420/2620 (Base) | 3 parts |
| • 0709/9000 (Activator) | 1 part |
| • 0491/9000 (Thinner) | 1 parts |

Specifications



0986/2620 is qualified to:

- AIMS 04-04-005
- TN-A-007-10106
- WL5.7030

Product Compatibility

0986/2620 is compatible with the following specifications:

- AIMS 04-04-002
- AIMS 04-04-011
- BS2X34A+B

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

0986/2620 Anti-Static Type II Kit

Surface Preparation and Pretreatment



Ensure that the correct surface pre-treatment has been carried out, and that drying and overcoat times are observed. Ensure the surface is clean, dry and intact using high performance solvent cleaner DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended.

Instructions for Use



Hand stir or shake the base component to ensure adequate dispersion. Add the activator to the base, thoroughly stir until a smooth uniform mix is obtained. Finally add thinner and stir well before use.

Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.



Induction Time:


Not required



Viscosity: (23°C/73°F)

• AFNOR4	18 - 25 seconds
• BSB3	20 - 47 seconds
• BSB4	20 - 26 seconds
• FORD4	16 - 22 seconds
• ISO4	30 - 45 seconds
• ZAHN2	21 - 29 seconds

Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.



Pot Life:

2 hours @ 21 - 25°C (70 - 77°F)

Application Guidelines

Recommended Application Conditions:

Temperature 15 - 30°C (59 - 86°F)
Relative Humidity 30 - 80%



0986/2620 Anti-Static Type II Kit

Application:

Apply several light coats to reach the recommended dry film thickness 40 - 55 μm .




Theoretical Coverage: (ready for use)

7 m² Lt @ 50 μm dry film thickness
280 ft² US gal @ 2 mil dry film thickness

Recommended Dry Film Thickness:

40 - 55 μm
1.6 - 2.2 mil



Dry Film Density:

1.7 g/cm³
14.2 lbs/US gal

Dry Film Weight:

85 g/m² @ 50 μm dry film thickness
0.017 lbs/ft² @ 2 mil dry film thickness

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

Equipment:



Equipment	Tip Size	Air Pressure
Pneumatic Application	15/10 mm	43.5 to 58 psi (3 to 4 bar)
Airless	0.33 mm	1740 to 1885 psi (120 to 130 bar)
Conventional Air Spray	1.5 mm	43 to 58 psi (3 to 4 bar)

Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

0986/2620 Anti-Static Type II Kit

Physical Properties



Colour:

Grey




Gloss:

Not applicable



Drying Times @ 50 % R.H.	23°C (73°F)	60°C (140°F)
Dry to Touch	90 minutes	
Dry to Handle	4 hours	30 minutes
Dry to Tape	8 to 10 hours	
Dry to Overcoat	1 to 72 hours	
Full Cure	7 days	3 hours

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.



Flash Off Time:

20 minutes at ambient temperature



VOC: (ASTM)

Mixed ready for use	560 g/Lt
5420/2620 Base Component	500 g/Lt
0709/9000 Activator	460 g/Lt
0491/9000 Thinner	840 g/Lt



Flash Point:

5420/2620 Base Component	29°C (84°F)
0709/9000 Activator	47°C (116°F)
0491/9000 Thinner	-3°C (27°F)



0986/2620 Anti-Static Type II Kit


Shelf Life:

5420/2620 Base Component	18 months in original unopened container
0709/9000 Activator	18 months in original unopened container
0491/9000 Thinner	10 years in original unopened container

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



0986/2620 Anti-Static Type II Kit

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200

Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119

Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666

Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

ASC - South Europe

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace

Sealants and Coatings

Darlington Road

Shildon, Co Durham UK

DL4 2QP

www.ppgaerospace.com

Issue Date: 08/15

Lit: 4289